

INDIAN ORIGIN FLY ASH REF #1.2 TEST ANALYSIS RESULTS

Test / Parameter	Unit	Method	Result
Moisture	% w/w	ASTM C311	0,05
Loss on ignition	% w/w	IS 1727:1967 (RA-2013)	0,49
Sulfuric Trioxide (SO ₃)	% w/w	IS 1727:1967 (RA-2013)	0,08
* Retained on 45 micron	% w/w	By sieve analysis	16,97
Silica (as SiO ₂)	% w/w	IS 1727:1967 (RA-2013)	62,68
Calcium (as CaO)	% w/w	SO-IN-MUL-TE-109 (by ICPOES)	0,92
Alumina (as Al ₂ O ₃)	% w/w	IS 1727:1967 (RA-2013)	26,11
Iron (as Fe ₂ O ₃)	% w/w	IS 1727:1967 (RA-2013)	4,7
Iron (as Fe)	% w/w	IS 1727:1967 (RA-2013)	3,47

Renelux believes the information contained herein is accurate; however, it makes no guarantees with respect to such accuracy and assumes no liability in connection with the use of the information contained herein.